

# AWTA PRODUCT TESTING

Australian Wool Testing Authority Ltd - trading as AWTA Product Testing  
A.B.N 43 006 014 106  
1st Floor, 191 Racecourse Road, Flemington, Victoria 3031  
P.O Box 240, North Melbourne, Victoria 3051  
Phone (03) 9371 2400 Fax (03) 9371 2499

## TEST REPORT

**Client :** UB Trading Pty Ltd  
13 Kirkton PI  
Edensor Park NSW 2176

**Test Number :** 18-005736  
**Issue Date :** 10/01/2019  
**Print Date :** 10/01/2019

**Sample Description** Clients Ref : "Aqua Stone - SPC Flooring"  
Flexible SPC Floor panels  
Lt Brown timber effect  
Nominal Composition : Stone Polymer Composite  
Nominal Thickness : 7mm

### AS/ISO 9239.1-2003 Reaction to Fire Tests for Floorings. Determination of the Burning Behaviour using a Radiant Heat Source

Date of Sample Arrival 27/09/2018  
Date Tested 10/01/2019

CHF Value	1	2	3	Mean
Length	≥11	-	-	- kW/m <sup>2</sup>
Width	≥11	≥11	≥11	- kW/m <sup>2</sup>
HF-30 Value	1	2	3	Mean
Length	-	-	-	- kW/m <sup>2</sup>
Width	-	-	-	- kW/m <sup>2</sup>
Smoke Value	1	2	3	Mean
Length	12	-	-	- %.min
Width	16	12	14	14 %.min

Blistering Yes

# AWTA PRODUCT TESTING

Australian Wool Testing Authority Ltd - trading as AWTA Product Testing  
A.B.N 43 006 014 106  
1st Floor, 191 Racecourse Road, Flemington, Victoria 3031  
P.O Box 240, North Melbourne, Victoria 3051  
Phone (03) 9371 2400 Fax (03) 9371 2499

## TEST REPORT

**Client :** UB Trading Pty Ltd  
13 Kirkton Pl  
Edensor Park NSW 2176

**Test Number :** 18-005736  
**Issue Date :** 10/01/2019  
**Print Date :** 10/01/2019

The test results relate to the behaviour of the test specimens of a product under the particular conditions of the test, they are not intended to be sole criterion for assessing the potential fire hazard of the product in use.

Sample was conditioned in accordance with BSEN 13238:2010 at a temperature of  $23\pm 2^{\circ}\text{C}$  and relative humidity of  $50\pm 5\%$  for a minimum of 48 hours prior to testing.

Each specimen was clamped to a substrate of 6mm thick fibre reinforced cement board prior to testing.

HF30 not reported as flame out time occurred before 30 minutes.

152866

31093

Page 2 of 2

© Australian Wool testing Authority Ltd  
Copyright - All Rights Reserved



Accredited for compliance with ISO/IEC 17025 - Testing  
- Chemical Testing  
- Mechanical Testing  
- Performance & Approvals Testing

: Accreditation No. 983  
: Accreditation No. 985  
: Accreditation No. 1356




Samples and their identifying descriptions have been provided by the client unless otherwise stated. AWTA Ltd makes no warranty, implied or otherwise, as to the source of the tested samples. The above test results relate only to the sample or samples tested. This document shall not be reproduced except in full and shall be rendered void if amended or altered. This document, the names AWTA Product Testing and AWTA Ltd may be used in advertising providing the content and format of the advertisement have been approved by the Managing Director of AWTA Ltd.

0204/11/06



APPROVED SIGNATORY



MICHAEL A. JACKSON B.Sc.(Hons)  
MANAGING DIRECTOR